## **AMENDMENTS TO THE CLAIMS**

This listing of claims replaces all prior versions of claims in the application.

1-16. (Cancelled)

17. (Currently Amended): The method according to claim 16, A method for producing a polyimide film comprising polyimide whose imidization ratio ranges from 98% to 100% and satisfying an optical characteristic condition represented by the formula (1) below:

 $nx > ny > nz \tag{1},$ 

wherein nx, ny and nz respectively indicate refractive indices in an X-axis direction, a Y-axis direction and a Z-axis direction in the polyimide film, with the X axis corresponding to an axial direction exhibiting a maximum refractive index within a surface of the polyimide film, the Y axis corresponding to an axial direction perpendicular to the X axis within the surface, and the Z axis corresponding to a thickness direction perpendicular to the X axis and the Y axis, the method comprising:

- (A) a step of applying a solution of polyimide having an imidization ratio of 98% to 100% onto a plastic base and drying the solution, thus forming a polyimide coating; and
- (B) a step of stretching the polyimide coating together with the plastic base so as to satisfy the formula (1) above,

wherein the plastic base comprises at least one selected from the group consisting of polyester, cellulose ester, polyolefin, substituted polyolefin, polycarbonate and polysulfone, and

Application No. 10/518,079

Attorney Docket No. 042890

wherein the polyester comprises at least one selected from the group consisting of

polyethylene terephthalate, polyethylene isophthalate, 1,4-cyclohexanedimethylene terephthalate,

polybutylene terephthalate and polyethylene naphthalate, the cellulose ester comprises at least

one selected from the group consisting of triacetylcellulose, cellulose propionate and cellulose

butyrate, the polyolefin comprises at least one selected from the group consisting of

polynorbornene, polyethylene, polypropylene and polystyrene, the substituted polyolefin

comprises at least one of isobutene-N-methylmaleimide copolymer and acrylonitrile-styrene

copolymer, the polycarbonate comprises at least one selected from the group consisting of

polycarbonate of bisphenol A, polycarbonate of bisphenol C (2,2-bis(4-hydroxyphenyl)-1,1-

of dichloroethylene), polycarbonate of alkylidenebisphenol and polycarbonate

cycloalkylidenebisphenol, the polysulfone comprises at least one selected from the group

consisting of polyethersulfone, polyarylethersulfone, polyphenylsulfone and bisphenol A

polysulfone.

18. (Currently Amended): An optical element, whose one surface or both surfaces are

laminated with [[the]] an optical film according to claim 6, comprising a polyimide layer formed

of a polyimide film, comprising polyimide whose imidization ratio ranges from 98% to 100%

and satisfying an optical characteristic condition represented by the formula (1) below:

nx > ny > nz

(1),

Page 3

wherein nx, ny and nz respectively indicate refractive indices in an X-axis direction, a Yaxis direction and a Z-axis direction in the polyimide film, with the X axis corresponding to an axial direction exhibiting a maximum refractive index within a surface of the polyimide film, the Y axis corresponding to an axial direction perpendicular to the X axis within the surface, and the Z axis corresponding to a thickness direction perpendicular to the X axis and the Y axis.

19. (Currently Amended): An image display apparatus, comprising [[the]] an optical film according to claim 6, comprising a polyimide layer formed of a polyimide film, comprising polyimide whose imidization ratio ranges from 98% to 100% and satisfying an optical characteristic condition represented by the formula (1) below:

$$nx > ny > nz$$
 (1),

wherein nx, ny and nz respectively indicate refractive indices in an X-axis direction, a Yaxis direction and a Z-axis direction in the polyimide film, with the X axis corresponding to an axial direction exhibiting a maximum refractive index within a surface of the polyimide film, the Y axis corresponding to an axial direction perpendicular to the X axis within the surface, and the Z axis corresponding to a thickness direction perpendicular to the X axis and the Y axis.

20. (Currently Amended): An image display apparatus, comprising [[the]] an optical element according to claim 7 whose one surface or both surfaces are laminated with the polyimide film, comprising polyimide whose imidization ratio ranges from 98% to 100% and satisfying an optical characteristic condition represented by the formula (1) below:

Amendment Application No. 10/518,079 Attorney Docket No. 042890

nx > n	v > nz	(	1	).	•

wherein nx, ny and nz respectively indicate refractive indices in an X-axis direction, a Y-axis direction and a Z-axis direction in the polyimide film, with the X axis corresponding to an axial direction exhibiting a maximum refractive index within a surface of the polyimide film, the Y axis corresponding to an axial direction perpendicular to the X axis within the surface, and the Z axis corresponding to a thickness direction perpendicular to the X axis and the Y axis.